

Nifty PRODUCTS

P.O. Box 161, Marlboro, NJ 07746-0161
4 Jocama Boulevard, Old Bridge, NJ 08857-9743
732-591-1140 800-631-2172
FAX: 732-591-8477

NIFTY STRETCH FILM SPECS

Manufacturing Process	Blown
Web Width	12" – 15" – 18"
Roll Length	1500 ft.
Film Yield	42,880 sq. in./lb.
Tensile @ Break MD	6900 psi
Tensile @ Break TD	4700 psi
Tensile @ Yield MD	1600 psi
Tensile @ Yield TD	1700 psi
Elongation MD	420%
Elongation TD	700%
Puncture Force	8.6 lbs
Puncture Energy	14 in-lb
Puncture Energy/Thickness	20 in-lbs/mil
Elmendorf Tear MD	160 g/mil
Elmendorf Tear TD	500 g/mil
Core Size	3" I.D.
Roll Diameter	6" O.D.

MD: Machine Direction

TD: Transverse Direction